



Flexipel™ HR-A325

Nonfluorinated Water Repellent

Overview

- Nonfluorinated water repellent developed for use on a broad range of textiles and nonwovens
- Substrates may include polyester, cotton, cotton/polyester blends, nylon, and fiberglass
- Static Water Repellency rating of 3-4 and Water Spray Rating of 80-90
- Non-combustible

Applications

- Treatment of textile substrates such as cotton, polyester, cotton/polyester blends, nylon, and fiberglass
- Treatment of nonwoven substrates such as polyester, nylon, and fiberglass

Technical Information

Flexipel HR-A325 is an anionic, aqueous polymer emulsion which imparts water repellency to fabrics and nonwovens. This product is compatible with most anionic co-finishing products.

Formulary

Flexipel HR-A325 is diluted for use, with a recommended starting point of 4% (as delivered) in water.

Applications of dip/nip or spray are recommended, followed by heat cure for mill application.

Typical Properties*

PROPERTY	VALUE
Appearance	Off-white Emulsion
Ionic Nature	Anionic
pH	2.5 to 5.0
Water solubility	Dispersible
Solids, %	28.0 to 32.0
Viscosity	100 cps Max.
Density@25°C	0.99 to 1.03 g/ml
Boiling point	est. 100°C
Flash point	Non-combustible
Storage	Protect from freezing
Shelf life	12 months

*Typical properties do not represent specifications.

Packaging and Handling

Flexipel HR-A325 is available in:
275 gallon totes (Net Wt. 2205 lbs) 55 gallon blue TH poly drums (Net Wt. 441 lbs)

5 gallon plastic pails (Net Wt. 40 lbs)

Refer to the Safety Data Sheet (SDS) for information on the safe use, handling, and disposal of this product.

DOT Classification: Non-Regulated

Whether you are looking for a replacement product or an ingredient for a specific attribute, give us a call. We can provide assistance based upon your particular formulation requirements and composition. Please feel free to contact us.

Flexipel HR-A325

Nonfluorinated Water Repellent

This information relates only to the specific material referred to herein and not to its use in combination with any other material or in any process, unless explicitly stated herein. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled; however, no warranty, guarantee or other representation is made as to its accuracy, reliability, or completeness, or regarding any liabilities arising from others' intellectual property rights. ID# 20240903. revision 2