



Flexisperse™ AM-210

Overview

- Provides Stain Blocking and Soil Resistance to soft surface protectors and cleaners
- Anionic aqueous polymer
- Extremely efficient at low use levels
- Readily dilutes in water
- Can be formulated with oil and water repellents to provide enhanced stain resistance
- Formulates readily with cleaning products to enhance stain and soil resistance of cleaned surfaces
- Freeze/Thaw Stable in concentrate and dilution
- WERCS ID number: 1547275
- WERCS Validation number: 1547275

Applications

- Carpet, Rug and Upholstery Cleaners: Spotters, Extraction, Low Moisture/Bonnet and Pre-spray
- Carpet, Rug and Upholstery Protectors

Technical Information

Flexisperse AM-210 provides exceptional stain and soil resistance to nylon and wool carpet fibers when applied as a component of cleaning or protection formulations. The product can be used to formulate soft surface cleaning products for extraction, mist and scrub, aerosol, and conventional low moisture applications. Fluorochemical soil, stain, oil and water repellents are easily co-applied. Use rate depends on cost parameters, level of performance desired, and substrate. Typical application rates for carpet fibers range from 0.5 to 3.0 percent by weight of solution for significant stain and soil resistance.

FORMULARY


Recommended usage rates vary from 0.5% to 3.0% Flexisperse AM-210 by weight of solution depending on the level of performance desired. Flexisperse AM-210 can be blended with cleaning formulations and protectors to provide stain and soil resist features.

Performance Data

The chart below graphically illustrates the stain resist benefit realized when Flexisperse AM-210 is incorporated into carpet cleaning formulations. When compared to an untreated control, a carpet that was extracted using a Flexisperse AM-210 cleaning formula developed a remarkably high level of stain resistance when immersed for two minutes in an aqueous solution of Red Dye Number 40. Following a water rinse and drying, the level of staining was measured using a spectrophotometer and reported in units of Delta E relative to unstained carpet. A lower ΔE as demonstrated in the illustration below corresponds to less residual stain left in the carpet.


Demonstration

The photographs show the protection provided to soft surfaces when treated with formulations containing Flexisperse AM-210.




(Demonstration)

In the demonstration above, a commercial grade nylon carpet sample was treated with a formulation containing Flexisperse AM-210 at 1.0% by weight of solution. The pH of the finished formulation was approximately 8.0. Once dry, the treated sample was tested for stain resistance relative to an untreated control. As the photograph demonstrates, the level of stain resistance, relative to control, is excellent. The photograph below demonstrates the high degree of dry soil resistance achieved on carpet using cleaning and protector formulas containing Flexisperse AM-210. In the demonstration below, a cleaning formulation, containing Flexisperse AM-210, was applied per ASTM D6540. The results of this accelerated soiling test show how Flexisperse AM-210 prevents soil from adhering to the fiber surface while the surrounding untreated carpet attracts soil at a normal rate.



Untreated Control

Flexisperse AM-210



Typical Properties

Packaging and Handling

Appearance	Clear Amber Liquid
Density @ 25°C	1.15 +/- 0.02 g/ml (9.6 lbs/gal)
pH	3.0 +/- 1.0
Boiling Point	Approx. 100°C
Odor	Mild

Flexisperse AM-210 is available in 275 gallon totes (Net Wt. 2500 lbs), 55 gallon drums (Net Wt. 500 lbs) and 5 gallon pails (Net Wt. 40 lbs).

DOT Classification is Non Regulated.

Refer to the Safety Data Sheet (SDS) for information on the safe use, handling, and disposal of this product.

This information relates only to the specific material referred to herein and not to its use in combination with any other material or in any process, unless explicitly stated herein. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled; however, no warranty, guarantee or other representation is made as to its accuracy, reliability, or completeness, or regarding any liabilities arising from others' intellectual property rights. 20240806